The LONGWAY General Series 2V batteries (100-3000Ah) are designed and developed using AGM technology and valve controlled sealing technology. They can meet conventional performance requirements, with a designed float charging life of over 15 years. The valve controlled non-spillable structure design allows safe use in any direction and is certified by sea and air freight. The battery performance also meets international standards. such as IEC60896-2012, UL1989.etc.



General Feature

- High reliability, safe without leakage, can be used in any position
- Excellent recovery performance after deep discharge
- Environmentally friendly products.
 Meet EU battery directive RoHS and REACH standards
- · Maintenance free
- Widely applicable temperature range, can be used at -20 °C~60°C
- Low self-discharge rate. The average monthly self-discharge rate of the battery is less than 2.5%

(It is recommended to recharge after storage for 6 months or before use)


Applications

- Electrical power system
- Solar system
- · Electrical test equipment
- Telecom & Network Equipment
- UPS, fire alarm & safe-protection
- Emergency lighting device; Alarm system
- · Robots and control machines and other

Performance

Nominal Voltage	2V (1cell)					
Capacity	@25 ℃					
10hr Rate (250A)	2500Ah @ to 1.75V/ceII					
5hr Rate (425A)	2125Ah @ to 1.70V/cell					
3hr Rate (625A)	1875Ah @ to 1.60V/ceII					
Weight	Approx (118 \pm 3%)kg (260.1lbs)					
Internal Resistance	Approx $0.10 m\Omega$ fully charged @25 $^{\circ}$ C					
Maximum Discharge Current	400A(3sec)					
Terminal	17					
Operating Temperature Range	Discharge:-20℃~60℃;Charge:0℃~50℃ Storage:-20℃~40℃					
Container Material	ABS(UL94 HB)/UL94-V0 Optional					

Dimensions



Length	491mm	19.3inch
Width	351mm	13.8inch
Height	344mm	13.5inch
Total height	383mm	15.1inch

Battery use

Cycle use

- 1. Limit the initial charging current to no more than 500A
- 2. Keep charging voltage at 2.40-2.50V/unit, and continue charging at least 3 hours after the charging current reduces to 50A toensure full charge
- 3. The compensation coefficient of charging voltage and temperature is -5mv/cell / $^{\circ}$ C

Float use


- 1. Limit the initial charging current to no more than 500A
- 2. Keep charging voltage at 2.25-2.30V/unit. When the voltage reaches the constant voltage, the current gradually decreases until the battery is fully charged and continues to charge
- 3. The compensation coefficient of charging voltage and temperature is -3mv/cell / $^{\circ}$











Kaiying Power Supply & Electrical Equip Co., Ltd Email: sales@longwaybattery.com
Tel:0595-68782266 Fax:0595-68782222 Website: http://www.longwaybattery.com
Add: Kaiying Industrial Area, Chengxiang Town, Anxi, Quanzhou, Fujian Province, China KY-IOP-LW2-2500 Bo. May 2023














Constant current characteristics(A,25℃)										
F.V/TIME	15min	30min	60min	2h	3h	5h	8h	10h	20h	100h
1.60	3375	2625	1400	926.2	667.4	469.4	329.9	266.4	133.2	31.72
1.65	3308	2573	1372	921.6	664.1	467.1	328.3	265.9	133.0	31.66
1.70	3240	2520	1344	917.1	660.8	464.8	326.6	264.1	132.0	31.44
1.75	3139	2441	1302	912.5	657.5	462.5	325.0	263.3	131.6	31.34
1.80	3078	2394	1277	894.3	644.4	453.3	308.8	262.5	131.3	31.25

Constant power discharge characteristic (W,25℃)										
F.V/TIME	15min	30min	60min	2h	3h	5h	8h	10h	20h	100h
1.60	6075	4856	2681	1704	1318	934.2	658.1	532.9	266.4	63.44
1.65	5954	4759	2627	1696	1312	929.6	654.9	531.8	265.9	63.31
1.70	5832	4662	2574	1687	1305	925.0	651.6	528.2	264.1	62.88
1.75	5650	4516	2493	1679	1299	920.4	648.4	526.6	263.3	62.69
1.80	5540	4429	2445	1645	1273	902.0	616.0	525.0	262.5	62.50







Kaiying Power Supply & Electrical Equip Co., Ltd Email: sales@longwaybattery.com Tel:0595-68782266 Fax:0595-68782222 Website: http://www.longwaybattery.com Add: Kaiying Industrial Area, Chengxiang Town, Anxi, Quanzhou, Fujian Province, China KY-IOP-LW2-2500 B0. May 2023